



GS-80

ECONOMICAL, HIGH STRENGTH,
ADMIX AMALGAM



HIGH STRENGTH NON-GAMMA 2 ADMIX ALLOY

The technically advanced, non-gamma 2 admix amalgam at an affordable price.

GS-80's high strength and positive dimensional change ensures longevity and patient satisfaction.

Over 200 million successful GS-80 restorations have been placed since its worldwide release in 1986.

**POSITIVE
DIMENSIONAL
CHANGE**

**CHOICE OF
CAPSULE SIZES
AND SETTING TIMES**

**HIGH COMPRESSIVE
STRENGTH**

OPTIMAL HANDLING CHARACTERISTICS

GS-80's consistent mix, ease of loading, placement in preparations, condensability, burnishability, quality of interproximal contact, carvability, and setting characteristics ensure the final restorations meet the needs of the operator.



ULTRAMAT 2

The dual voltage Ultramat 2 with a high precision microprocessor controlled timer provides consistent and accurate trituration, ensuring the optimal handling and clinical characteristics of mixed materials.




HIGH STRENGTH AND POSITIVE DIMENSIONAL CHANGE

HIGH COMPRESSIVE STRENGTH


GS-80's high compressive strength minimizes the risk of fracturing the restoration⁽¹⁾. High compressive strength ensures a tough and durable long lasting restoration.

COMPRESSIVE STRENGTH @ 1 HOUR ⁽¹⁾



POSITIVE DIMENSIONAL CHANGE

GS-80's positive dimensional change ensures excellent sealing qualities at the margins⁽¹⁾. Negative values can contribute to post operative sensitivity.



GREATER CHOICE OF SETTING TIMES AND LARGER CHOICE OF CAPSULE SIZES

The working and setting times allow large restorations to be condensed and carved without difficulty.




PHYSICAL PROPERTIES

Composition:	Ag 40%, Sn 31.3%, Cu 28.7%, Hg 47.9%
Alloy Particle:	Spherical and Lathe Cut
Compressive strength @ 1 hour:	225MPa [32,625psi]
Compressive strength @ 24 hours:	510MPa [73,950psi]
Diametral tensile strength @ 1 hour:	22MPa [3,190psi]
Diametral tensile strength @ 24 hours:	54MPa [7,830psi]
Static creep @ 7 days:	0.1%
Dimensional change @ 24 hours:	+2µm/cm

CAPSULE SYSTEM

The SDI capsule system is designed to give consistent and accurate mixes every mix.




CONVENTIONAL CAPSULES

The plunger denotes the spill size:




The capsule body denotes the setting speed:



NOTE: 5 Spill only available in regular set.

ORDER DETAILS



GS-80 CAPSULES

Boxes of 50 capsules - One Spill 400mg alloy	
Slow Set	4401404
Regular Set	4401403
Fast Set	4401402
Boxes of 50 capsules - Two Spill 600mg alloy	
Slow Set	4402404
Regular Set	4402303
Fast Set	4402202
Boxes of 50 capsules - Three Spill 800mg alloy	
Slow Set	4403404
Regular Set	4403303
Fast Set	4403202
Boxes of 50 capsules - Five Spill 1200mg alloy	
Regular Set	4405000
Jars of 500 capsules - One Spill 400mg alloy	
Slow Set	4421404
Regular Set	4421403
Fast Set	4421402
Jars of 500 capsules - Two Spill 600mg alloy	
Slow Set	4422404
Regular Set	4422303
Fast Set	4422202
Jars of 500 capsules - Three Spill 800mg alloy	
Slow Set	4423404
Regular Set	4423303
Fast Set	4423202
Jars of 500 capsules - Five Spill 1200mg alloy	
Regular Set	4425000



GS-80 ALLOY TABLETS

Regular set 5oz	4450303
Regular set 1oz	4450505
Regular set 150g	4440303
Regular set 30g	4440304


GS-80 ALLOY POWDER

Regular set 5oz	4460303
Regular set 30g	4470303
Regular set 50g	4480303
Regular set 250g	4960303

GS-80 capsules conform to ISO 24234, ANSI/ADA Specification No.1.

*Amalcap Plus, Contour, Stratosphere and Premium are not the registered trademarks of SDI Limited.

[1] Source-Published and SDI test data.



EQUIPMENT

Ultramat 2 (USA - includes power cord for USA)	5546045
Ultramat 2 (All countries - includes power cord for the region the product is shipped to)	5546052
Ultramat S (All countries - includes power cord for the region the product is shipped to)	5546058



YOUR SMILE. OUR VISION.



MADE IN AUSTRALIA
by SDI Limited
3-15 Brunsdon Street,
Bayswater, Victoria 3153
www.sdi.com.au

AUSTRALIA 1800 337 003
AUSTRIA 00800 022 55 734
BRAZIL 0800 770 1735
FRANCE 00800 022 55 734
GERMANY 0800 100 5759

ITALY 00800 0225 5734
NEW ZEALAND +64 21 400 323
SPAIN 00800 022 55 734
UNITED KINGDOM 00800 022 55 734
USA & CANADA 1 800 228 5166